



(19)

(11) Publication number:

**58114730**

Generated Document.

**PATENT ABSTRACTS OF JAPAN**(21) Application number: **56209830**(51) Intl. Cl.: **B01J 23/10 C07C 29/15 C07C 31/04**(22) Application date: **28.12.81**

(30) Priority:

(43) Date of application  
publication: **08.07.83**(84) Designated contracting  
states:(71) Applicant: **TOKUYAMA SODA CO LTD**(72) Inventor: **MOMOSE HIROO  
MARUTANI KENICHI**

(74) Representative:

**(54) CATALYST FOR  
SYNTHESIS OF METHANOL**

(57) Abstract:

**PURPOSE:** To provide a catalyst for synthesis of methanol having high activity even under low pressure by using zirconium oxide and cerium oxide as main constituting components.

**CONSTITUTION:** The precipitate obtd. by causing reaction of solns. of salts of Zr and Ce in the presence of a precipitating agent is calcined or a salt of Ce is deposited on ZrO<sub>2</sub> and is heated and decomposed in air, whereby a catalyst consisting of ZrO<sub>2</sub> and CeO having 0.1W30wt% ratio in CeO/(ZrO<sub>2</sub>+CeO<sub>2</sub>) is obtd. Prior to synthesis of methanol from gaseous mixtures of CO/H<sub>2</sub>, or from such gaseous raw materials mixed further with inert gases such as N<sub>2</sub> and Ar, small amts. of gaseous CO<sub>2</sub> and CH<sub>4</sub> by using such catalyst, the catalyst is treated by heating in an atmosphere free from the atmospheric air, whereby the catalytic activity is improved. Said

**RECEIVED**  
APR 19 2002  
**TC 1700**